



PORIT-PLANSTEINE

Porenbeton-Plansteine nach DIN V 4165-100 oder nach DIBt-Zulassung

Bezeichnung	Druckfestigkeitsklasse	Rohdichteklasse	λ_R W/mK	Länge mm	Breite mm	Höhe mm	
▶ PPW 2 – 0,35	2	0,35	0,09	399 499 624	175	199	
					240		
					300		
					365		
					400		
	425	249					
	480						
▶ PPW 2 – 0,40	2		0,40	0,10	399 499 624	150	199
						175	
						200	
		240					
		300					
	365	249					
▶ PPW 2 – 0,50	2		0,50	0,14	624	115	249
						175	
▶ PPW 4 – 0,50	4		0,50	0,12	499 624	150	249
						175	
		200					
		240					
		300					
	365	249					
▶ PPW 4 – 0,50	4		0,50	0,13	499	150	249
						175	
						200	
						240	
		300					
	365	374					
▶ PPW 4 – 0,50	4		0,50	0,16	624	115	249
						374	
▶ PPW 4 – 0,55	4		0,55	0,13	399 624	150	249
						175	
		200					
		240					
		300					
	365	374					
▶ PPW 4 – 0,60	4		0,60	0,16	499 624	115	249
						150	
						175	
						240	
▶ PPW 6 – 0,60	6	0,60	0,16	499 624	115	249	
					150		
					175		
					240		
▶ PPW 6 – 0,65	6	0,65	0,18	399 499 624	115	249	
					150		
					175		
					200		
					240		
	300	374					
	365						

Bitte regionales Lieferprogramm beachten



PORIT-PLANSTEINE

Porenbeton-Plansteine nach DIN V 4165-100 oder nach DIBt-Zulassung

